



### **INTRODUCTION**

OZARK extrudes insulators from MgO, Al<sub>2</sub>O<sub>3</sub>, and HfO<sub>2</sub> for use in production of mineral insulated thermocouple cable, cartridge heaters, and other high temperature and electrical applications. Extrusion is a ceramic manufacturing technique which produces any shape with a constant cross section and theoretically unlimited length. A mix containing the desired ceramic powder and various organic additives is forced through a die opening configured to give the required geometry which may include holes of precise shape and size. The extrudate is subsequently dried, fired, cut, inspected and packaged for shipment. Precise control of process variables is required to obtain high quality extrusions meeting purity, microstructural, and dimensional specifications.

**CRUSHABLE INSULATORS** - These insulators, also known as preforms or cores, are designed to be easily crushed in the manufacturing operation. They are referred to interchangeably as crushable, soft-fired, or swageable. They may be designed to crush very easily to protect soft platinum components, or with more integrity to improve handling and performance properties. Please refer to the strength specifications.

**HARD-FIRED INSULATORS** – These insulators are meant to be suitable for free standing use without a metallic sheath or support. Standard dimensional tolerances for hard-fired insulators are more liberal. Hard fired extrusions may find other applications in metallurgical, mechanical, and refractory applications.

**MATERIAL/PURITY** - See specifications for purity analysis of standard magnesium oxide and aluminum oxide grades. Other materials are available on request or by custom order.

The following are typical analyses or limits for powders used to produce extruded insulators. All raw materials are high quality fused grain powders which are processed in-house to obtain optimum particle size distributions for end use as crushable or swageable thermocouple insulators.

CONTENT	CUM MgO	CHM MgO	CTM MgO	CCA Al <sub>2</sub> O <sub>3</sub>	CUH HfO <sub>2</sub>
MgO (%)	99.85	99.47	97.44	.0003	ND
Al <sub>2</sub> O <sub>3</sub> (%)	0.01	0.03	0.36	99.99	.050
SiO <sub>2</sub> (%)	0.04	0.12	1.41	0.005	<.02
Fe <sub>2</sub> O <sub>3</sub> (%)	0.04	0.06	0.06	0.003	<.02
CaO (%)	0.05	0.31	0.73	0.001	ND
B (PPM)	3	25	<30	ND	ND
Cd (PPM)	<10	<10	<30	ND	ND
S (PPM)	<10	<10	<10	ND	ND
C (PPM)	<10	<10	<10	ND	ND

**STRENGTH** – Insulators are fired to uniform mechanical strengths which have been established for optimum handling and swaging characteristics for different applications. The present test standard is the Modulus of Rupture (MOR) test. OZARK offers the following guidelines for MOR spec ranges:

MOR range	Description	Grades	Recommended Uses
2000-4000	soft	SHM, CCA	Platinum thermocouple, >.75" OD thermocouple
3000-6000	medium soft to medium	CHM, CTM	Thermocouple
4000-8000	medium	CTM	Thermocouple, coil heater on ID, Cold Core
5000-10000	medium hard	CTM	Cartridge Wind Core, Cold Core
7000-12000	hard	BTM	small OD Cartridge Core, tubular core, spacer stock

MOR values are psi as measured by a three point flexural beam tester.





The following information indicates some of the principles for acceptable design limits and the most cost-effective design parameters. This is intended as a guide for developing hole sizes and positions for best production efficacy, but external factors may require compromises with production ideals.

**O.D. (OUTSIDE DIAMETER)** – Nominal O.D. sizes may be specified to the nearest .001” increment from 0.030” to 1.250 inch for crushable insulators, and from 0.030” to about 0.500” for hard fired insulators. OZARK has over 300 round dies in inventory, including most sizes up to 0.5”. Modest tool charges (about \$200 per inch OD size) may apply for parts over 0.5” if a nearby size is not available.

Non-round parts are made in shaped dies, and there are fewer sizes available in-house. OZARK maintains blanks which can be finished with good turnaround times, at a price of about \$300/inch dimension.

Default Tolerances- the larger of +/- .003 inch or one percent of the nominal dimension. The O.D. is determined as the average diameter of the part measured in at least two places. The OD of the lot is considered within spec if the average OD of the lot is within the tolerance limit.

**I.D. (HOLE SIZE)** - The minimum standard hole size is the lesser of .010 inch, or 15% of the OD. Smaller holes ratios can be produced with less control of the hole position. The Maximum hole size is dictated by the wall and web thickness criteria (see table below). Closely spaced holes may result in “teardrop” shaped holes, or web knitting problems.

Default Tolerances- .002 inch plus 2% of the nominal hole size. Example: For a .050 hole size, the hole tolerance is computed at .003 inch, because .002 + (2% x .050) = .003. The hole size is defined as the largest pin gage size (to the nearest .001 inch) that slides freely through the part.

**CONFIGURATION and BOLT CIRCLE** - Standard configurations are defined by having equal web and wall spacings. Symmetric designs are preferable, but not mandatory.

Thin webs and walls lead to misshapen holes due to the tendency to collapse into the neighboring hole. Insulator shape cannot be guaranteed for wall or web thickness less than the hole size. The minimum size limit for wall and web thickness is 50% of the neighboring hole size. Large holes may result in loss of roundness and potential for thin webs and/or walls. The following table indicates the suggested hole size for a standard geometry as a multiple of the O.D.

NUMBER OF HOLES	1	2	3	4	5	6	7	8
IDEAL I.D. = O.D. X	.333	.200	.188	.171	.156	.142	.131	.122
MAXIMUM I.D.÷ O.D.	.700	.286	.268	.243	.220	.200	.183	.169

Any other configuration may be specified within fabrication limitations. Center holes may be added, and unequal hole sizes may be specified. Please contact us with your request for optimum design specifications for special configurations.

**LENGTH** – Any nominal length may be specified between 0.5 and 9.5”. There is a premium for lengths under 2” or over 8”, and for L/D ratios over 30. If your specs permit a small percentage at a shorter length, then the production yield will improve by the reworking of chips and small flaws.

Default Tolerances- There are no standard specifications for length unless requested by the user. Normally parts are cut in three-inch and/or four-inch lengths within +0.25 / -0 inch tolerance.

**STRAIGHTNESS** - Camber is inspected by rolling the insulators between plates of glass set at the maximum permissible spacing as determined by the operating spec and the nominal length of the parts.

Default Tolerances- The default tolerance for crushable thermocouple insulators is .003 in/in. The default tolerance for heater grade products is .006 in/in. All hard fired insulators are on a “best efforts” basis unless otherwise specified, and OZARK recommends a design cushion of .005 in/in.

**TWIST** - Twist is overchecked by spot inspection of samples for the lot.

Default Tolerances- Crushable insulators may have up to 5 degrees/inch. Heater products are to average less than 20 degrees per full length. Hard fired insulators may be up to 10 degrees/inch.

**Ozark Technical Ceramics, Inc. 402 Ware St. Webb City, MO 64870-2789  
Tel. (417) 673-2463 / FAX (417) 673-2464 / website: [www.ozarktech.com](http://www.ozarktech.com)**

